

cited in the European Search
Report of EP04789566.7
Your Ref.: H2260-EOA

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
18 July 2002 (18.07.2002)

PCT

(10) International Publication Number
WO 02/055599 A2

(51) International Patent Classification⁷: C08L 23/00

(21) International Application Number: PCT/NL02/00006

(22) International Filing Date: 7 January 2002 (07.01.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/756,290 9 January 2001 (09.01.2001) US

(71) Applicant (for all designated States except US): DSM N.V.
[NL/NL]; Het Overloon 1, NL-6411 TE Heerlen (NL).

(72) Inventors; and

(75) Inventors/Applicants (for US only): WILLEMS, Edwin
[NL/NL]; Rolandsweg 8, NL-6136 BV Sittard (NL).
SADEGHI, Mohammad, Reza [US/US]; 70 Holland
Woods Road, Leominster, MA 01453 (US).

(74) Agent: DORRESTIJN, Antoon; DSM Patents & Trade-
marks, P.O. Box 9, NL-6160 MA Geleen (NL).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM,
HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK,
LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX,
MZ, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL,
TI, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW).
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM).
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR). OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR,
NE, SN, TD, TG).

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.



WO 02/055599 A2

(54) Title: THERMOPLASTIC ELASTOMER COMPOSITION AND MOLDED ARTICLES MADE THEREOF

(57) Abstract: The subject invention relates to a thermoplastic elastomer composition that contains a dynamically vulcanized ther-
moplastic elastomer (a) on the basis of a polypropylene polymer and an at least partly dynamically vulcanized rubber, a thermoplastic
polyester block copolymer (b) and a compatibilizer (c). The rubber is preferably an EPDM or EPM copolymer. The thermoplastic
polyester block copolymer is preferably a polyether ester block copolymer. The thermoplastic elastomer composition according to
the invention for instance contains 20-80 parts (a), 80-20 parts (b), and 1-40 parts (c), the sum of the parts (a+b+c) being 100. The
thermoplastic elastomer composition according to the invention also relates to molded articles that contain the thermoplastic elas-
tomer composition.

WO 02/055599

PCT/NL02/00006

- 1 -

THERMOPLASTIC ELASTOMER COMPOSITION
AND MOLDED ARTICLES MADE THEREOF

5

The invention relates to a thermoplastic elastomer composition and molded parts thereof.

A thermoplastic elastomer composition is known inter alia from
10 Polymer Blends, Volume 2: Performance, edited by D.R. Paul and C.B. Bucknall, ISBN 0-471-35280-2, 2000. This article describes thermoplastic elastomers on the basis of a thermoplastic polymer and a dynamically vulcanized rubber which is dispersed in a continuous phase of the thermoplastic polymer in the form of fine particles. Such thermoplastic elastomers, thermoplastic vulcanisates, hereinafter
15 called (TPV's), possess a number of properties of an elastomer and can be processed among other things as a thermoplastic polymer.

The most widely used TPV's have a polyolefin as thermoplastic polymer. As a consequence, these TPV's adhere only to apolar substrates and they do not adhere, or only with difficulty, to polar substrates. To improve the adhesion, the
20 substrate is often pretreated. Industrially used pretreatment methods are dependent on the substrate and may for instance be chromic acid etching, ozone treatment, UV irradiation, primer coatings or plasma treatment. However, these pretreatments are expensive, use hazardous substances, result in product degradation and involve environmental risks.

25 The aim of the present invention is to provide a thermoplastic elastomer composition that exhibits intrinsically good adhesion to polar and apolar substrates while it does not have the above-mentioned disadvantages.

This aim is achieved according to the invention with a thermoplastic elastomer composition that contains a blend of:

- 30 a. a dynamically vulcanized thermoplastic elastomer containing a polypropylene polymer and an at least partly dynamically vulcanized rubber
b. a thermoplastic polyester block copolymer
c. a compatibilizer.

It has, surprisingly, been found that the thermoplastic elastomer
35 composition according to the invention exhibits particular good adhesion both to apolar and to polar substrates, whereby it is possible to leave out the

WO 02/055599

PCT/NL02/00006

- 2 -

pretreatment of the substrate.

A further advantage is that the thermoplastic elastomer composition is obtained with a relatively low hardness and good mechanical properties. Yet another advantage is that the thermoplastic elastomer composition according to the invention shows a good chemical resistance towards several chemicals. Yet another advantage is that molded articles from the composition according to the invention show a very good grip and soft touch, which makes the thermoplastic elastomer composition very suitable for the production of for example hand grips. From US-A-5149589, a composition is known comprising a thermoplastic elastomer and a copolyester. However the composition only shows a good adhesion to polar substrates. The composition has no good resistance to chemicals. Moreover the molded articles have no good grip and soft touch.

Examples of suitable polypropylene polymers used in the thermoplastic elastomer composition according to the invention are thermoplastic polypropylene homo- and copolymers or blends thereof. Examples are polypropylene homopolymers or polypropylene copolymers with max 30 % polyethylene or copolymers of propylene and an alpha-olefin with 4-12 carbon atoms. Preferably the polypropylene homopolymer is used. The polypropylene may be atactic, isotactic, syndiotactic or a physical and chemical mixture thereof. The term chemical mixture means that the polypropylene may have atactic, isotactic or syndiotactic structures randomly or in blocks along the molecular chains. The polypropylene homopolymer may be linear or branched. The Melt flow index (MFI) of the polypropylene preferably is between 0.3 and 50; more preferably below 20 (according to ISO norm 1133 (230°C; 2.16 kg load)).

Examples of rubbers that can be used in the thermoplastic elastomer composition according to the invention are rubbers that are suitable for dynamic vulcanization. Examples of such rubbers are ethylene-propylene copolymers, hereinafter called EPM, ethylene-propylene-diene terpolymers, hereinafter called EPDM, styrene butadiene rubber, nitrile butadiene rubber, isobutene-isoprene rubber, styrene-ethylene/styrene-butadiene block copolymers, butyl rubber, isobutylene-p-methylstyrene copolymers or brominated isobutylene-p-methylstyrene copolymers, natural rubber or blends of these. Preferably, EPDM or EPM is used as rubber. Most preferably, EPDM is used as rubber. The EPDM preferably contains 50-70 parts by weight ethylene monomer

WO 02/055599

PCT/NL02/00006

- 3 -

units, 48-30 parts by weight monomer units originating from an alpha-olefin and 2-12 parts by weight monomer units originating from a non-conjugated diene. As alpha-olefin use is preferably made of propylene. As non-conjugated diene use is preferably made of dicyclopentadiene (DCPD), 5-ethylidene-2-norbornene (ENB) or vinylnorbornene (VNB).

The dynamic vulcanization of the rubber is carried out in the presence of a suitable vulcanization agent such as for instance sulfur, sulfurous compounds, metal oxides, maleimides, phenol resins or peroxides. These vulcanization systems are known from the state of the art and are described in US-A-5100947. It is also possible to use siloxane compounds as vulcanization agent, examples are hydrosilane or vinylalkoxysilane. The thermoplastic elastomer composition according to the invention is preferably vulcanized with the aid of phenol resins, siloxanes or peroxides as vulcanization agent. The degree of vulcanization can be expressed in terms of gel content. This method is described in US-A-5100947.

The rubber in the thermoplastic elastomer composition according to the invention is at least partly vulcanized and for instance has a gel content between 60 and 100%. More preferably, the rubber has a gel content between 80 and 100%. Most preferably, the rubber is fully vulcanized and has a gel content in excess of 95%.

The polyester block copolymer used in the thermoplastic elastomer composition according to the invention preferably consists of soft blocks of a flexible polymer segment and hard blocks of a non flexible polymer segment.

The soft blocks of the flexible polymer segments for instance have a molecular mass of 400-6000 g/mol; preferably they have a molecular mass of 500-3000 g/mol. Examples of soft blocks are aliphatic polyether segments or aliphatic polyester segments. Examples of aliphatic polyester segments are polybutylene adipate segments or polycaprolactone segments. Examples of aliphatic polyether segments are polyalkylene-oxide glycol segments such as for instance polyethylene-oxide glycol segments, polypropylene-oxide glycol segment, polytetramethylene-oxide glycol segments or ethylene oxide-terminated polypropylene-oxide glycol segments.

Preferably, an aliphatic polyether segment is used as soft block in the polyester block copolymer. More preferably, ethylene oxide-terminated polypropylene-oxide glycol segments or polytetramethylene-oxide glycol segments are used.

The hard blocks in the polyester block copolymer preferably

WO 02/055599

PCT/NL02/00006

- 4 -

consist of repeating units of at least one alkylene glycol and at least one aromatic dicarboxylic acid or an ester thereof. The alkylene group generally contains 2-6 carbon atoms, preferably 2-4 carbon atoms. Examples are ethylene glycol, propylene glycol or butylene glycol. Preferably, use is made of propylene glycol or butylene glycol. More preferably, use is made of butylene glycol. Examples of aromatic dicarboxylic acids are terephthalic acid, isophthalic acid, 1,4-naphthalene dicarboxylic acid or 4,4'-diphenyl dicarboxylic acid. Examples of the hard polyester blocks are polyethylene terephthalate segments, polypropylene terephthalate segments or polybutylene terephthalate segments. Preferably, polybutylene terephthalate segments are used as hard polyester block.

The ratio between the soft and hard blocks in the polyester block copolymer can generally vary within wide limits, but is chosen in particular in light of the desired hardness of the polyester block copolymer. The hardness may generally vary between 20 and 80 Shore D.

Most preferably, the polyester block copolymer is a block copolymer with hard blocks derived from polybutylene terephthalate segments and soft blocks derived from polytetramethylene-oxide glycol segments or ethylene oxide-terminated polypropylene-oxide glycol segments.

The polyester block copolymer may further contain the customary additives such as stabilizers, colorants, processing aids or flame-retarding compounds.

Examples and the preparation of polyester block copolymers are described inter alia in Handbook of Thermoplastics, ed. O. Olabishi, Chapter 17, Marcel Dekker Inc., New York 1997, ISBN 0-8247-9797-3, in Thermoplastic Elastomers, 2nd Ed, Chapter 8, Carl Hanser Verlag (1996) ISBN 1-56990-205-4, and in Encyclopedia of Polymer Science and Engineering, Vol. 12, Wiley & Sons, New York (1988), pp. 75-117 and the references given there.

The compatibilizer (c) in the thermoplastic elastomer composition according to the invention is compatible with both the dynamically vulcanized thermoplastic elastomer (a) and the thermoplastic polyester block copolymer (b).

Compatibilizers that can be used in the thermoplastic elastomer composition according to the invention are functionalized polymers such as for instance epoxy or acid functionalized polymers. Preferably the epoxy or acid functionalized polymers are epoxy or acid functionalized olefine polymers. Examples of epoxy functionalized olefine polymers are copolymers of ethylene-glycidyl methacrylate

WO 02/055599

PCT/NL02/00006

- 5 -

or ethylene-glycidyl acrylate or terpolymers of ethylene-glycidyl methacrylate-acrylate or glycidyl methacrylate functionalized polyethylene or glycidyl methacrylate functionalized acrylate terpolymers. Examples of acid functionalized olefine polymers are maleic anhydride functionalized olefine polymers such as maleic anhydride functionalized polypropylene or maleic anhydride functionalized polyethylene. Preferably, an epoxy functionalized olefin polymer is used as compatibilizer in the thermoplastic composition according to the invention.

The thermoplastic elastomer composition according to the invention for instance contains 20-80 parts (a), 80-20 parts (b) and 1-40 parts (c) the sum of the parts (a+b+c) being 100. Preferably, the thermoplastic elastomer composition according to the invention contains 30-70 parts (a), 70-30 parts (b) and 5-20 parts (c), the sum of the parts of (a+b+c) being 100.

The thermoplastic elastomer composition according to the invention optionally contains other customary additives. Examples of such additives are reinforcing and non-reinforcing fillers, plasticizers, antioxidants, stabilizers, oil, antistatic agents, waxes, foaming agents, pigments, flame retardants and other known agents and are described in the Rubber World Magazine Blue Book, and in Gaether et al., *Plastics Additives Handbook*, (Hanser 1990). Examples of fillers that can be used are calcium carbonate, clay, silica, talc, titanium dioxide, and carbon. Examples of oil that can be added are paraffinic oil, naphthenic oil or aromatic oil obtained from petroleum fractions. Another additive that can optionally be added to the thermoplastic composition according to the invention is a Lewis base such as for instance a metal oxide, a metal hydroxide, a metal carbonate or hydrotalcite.

The additives can be added during the preparation of the TPV or during the preparation of the thermoplastic elastomer composition according to the invention or during both. The quantity of additive to be added is known to one skilled in the art.

The thermoplastic elastomer composition can be prepared via two successive steps but can also be prepared in one step. If the thermoplastic elastomer composition is prepared in two successive steps, in a first step the TPV will be prepared by blending the polypropylene polymer, the rubber and other additives customarily employed by one skilled in the art in for instance a Brabender blender. After these components have been properly dispersed, the

WO 02/055599

PCT/NL02/00006

- 6 -

vulcanization agent is added to initiate the dynamic vulcanization. This blend results in a TPV. In a second step the TPV is introduced into an extruder and blended with the polyester block copolymer and the compatibilizer. These two steps can be carried out independently as separate steps or sequentially in the same equipment. It is also possible for the thermoplastic elastomer composition according to the invention to be prepared in a single step, with the TPV, the polyester block copolymer and the compatibilizer being introduced simultaneously into the extruder and be blended further with the additives customarily employed by one skilled in the art. It is also possible to prepare a TPV in a first step, which is subsequently blended with a compatibilizer in the same extruder. Next, the resulting TPV masterbatch can be blended with the polyester block copolymer.

The thermoplastic elastomer composition according to the invention can for instance be blended with one or more polymers chosen from styrene-butadiene-styrene rubber (SBS), styrene-ethylene/styrene-butadiene block copolymers (SEBS), styrene-propylene-styrene terpolymers (SPS), styrene-isopropylene-styrene terpolymers (SIPS), polyvinyl chloride, polycarbonate, acrylonitrile-butadiene-styrene terpolymers, polybutylene terephthalate, polypropylene, styrene-acrylonitrile copolymers, styrene-maleic anhydride copolymers, polyphenylene oxide, or polyethylene. This for instance involves adding 1-40 parts of the above-mentioned polymers relative to the parts of the total composition (a+b+c). Preferably, 1-20 parts of the above-mentioned polymers are added relative to the parts of the total composition (a+b+c).

The invention also relates to molded articles that contain the thermoplastic elastomer composition according to the invention. The invention particularly relates to molded articles comprising a substrate part and a part that comprises the thermoplastic elastomer according to the invention whereby the parts are being adhered. It has been found that the thermoplastic elastomer composition according to the invention exhibits particularly good adhesion to both polar and apolar substrates. Preferably, the adhesion between the thermoplastic elastomer composition according to the invention and the substrate is such that cohesive failure takes place, both when the substrate is polar and when it is apolar. Cohesive failure takes place when the adhesion between the thermoplastic elastomer composition according to the invention and the substrate is stronger than the thermoplastic elastomer composition.

The molded articles can be prepared using processing methods customarily

WO 02/055599

PCT/NL02/00006

- 7 -

employed by one skilled in the art, examples being co-extrusion, blow molding of two or more components, injection molding of two or more components, robotic extrusion, or injection overmolding.

- The thermoplastic elastomer composition according to the
- 5 invention can for instance be used in door profiles, wire & cables, hoses, dashboard films, window encapsulation and soft touch grips.

The invention will be elucidated with reference to the following examples, without being limited thereto.

- 10 The materials used in the examples are the following:
Amitel™ EM400 (38 Shore D copolyether ester, DSM)
Amitel™ EM550 (55 Shore D copolyether ester, DSM)
Amitel™ EM630 (63 Shore D copolyether ester, DSM)
TPV40 (40 Shore A PP-EPDM-oil TPV)
- 15 Lotader™ AX8840 (GMA functionalized PE, Elf Atochem)
Lotader™ AX8860 (terpolymer of ethylene, acrylic ester and glycidyl methacrylate (GMA), Elf Atochem)
Lotader™ AX8930 (GMA functionalized acrylate terpolymer, Elf Atochem)
- 20 The measurements in the examples were carried out using the following tests:
Hardness DIN 53505
Mechanical properties ISO 37
Compression set ISO 815

25 Example 1

TPV40 is produced by melt blending 45% EPDM, 10% PP, 35% paraffinic oil, 0.5% phenolic resin, 0.5% stannous chloride and 0.5% stabilizer on a 40mm co-rotating twin screw extruder at a melt temperature of 250°C.

- In a second step the thermoplastic elastomer composition is
- 30 produced by melt blending the TPV40 with a copolyether ester (Amitel™ EM400) and an epoxy functionalized compatibilizer (Lotader™ 8860) on a 30mm co-rotating twin screw extruder at a melt temperature of 230°C.

The adhesion properties are tested by co-extruding 1 mm strip of the thermoplastic elastomer composition on top of different substrates (2mm of

WO 02/055599

PCT/NL02/00006

- 8 -

polycarbonate, ABS and polypropylene) at a temperature of 220°C. The adhesion after co-extrusion is evaluated by ranking the peel strength and is classified as either no, poor or strong adhesion and the type of failure is classified as either adhesive or cohesive.

- 5 The mechanical properties and adhesion results are shown in table 1.

Comparative example A

- 10 The same procedure as in example 1 is followed but instead of an epoxy functionalized compatibilizer no compatibilizer is used. The mechanical properties and adhesion results are shown in table 1.

Comparative example B

- 15 The same procedure as in example 1 is followed but no copolyether ester is added. The mechanical properties and adhesion results are shown in table 1.

Comparative example C

- 20 The same procedure as in example 1 is followed but no TPV-40 is added. The mechanical properties and adhesion results are shown in table 1.

WO 02/055599

PCT/NL02/00006

- 9 -

Table 1

	A	B	C	1
Composition				
Arnitel™ EM400	50%		90%	50%
TPV-40	50%	90%		40%
Lotader™ AX8860		10%	10%	10%
Mechanical properties				
Hardness [Shore A]	75	41	98	75
Tensile strength [Mpa]	1.3	3.9	14.1	6.5
Elongation [%]	95	310	510	330
Adhesion onto PC	Poor	No	Strong	Strong
Type of failure	Adhesive	Adhesive	Cohesive	Cohesive
Adhesion onto ABS	Poor	No	Strong	Strong
Type of failure	Adhesive	Adhesive	Cohesive	Cohesive
Adhesion onto PP	Poor	Strong	No	Strong
Type of failure	Adhesive	Cohesive	Adhesive	Cohesive

5 From table 1 it is clear that in comparative examples A, B and C there is no or poor adhesion to polar and apolar substrates. The type of failure is in most cases adhesive instead of cohesive. In example 1 very good adhesion to polar and apolar substrates was found, while the type of failure was cohesive in every case.

10

Examples 2 to 6

TPV40 is produced by melt blending 45% EPDM, 10% PP, 35% paraffinic oil, 0.5% phenolic resin, 0.5% stannous chloride and 0.5% stabilizer on a 40mm co-rotating twin screw extruder at a melt temperature of 250°C. In the

WO 02/055599

PCT/NL02/00006

- 10 -

same extrusion step the copolyether ester (Amitel™EM400) and an epoxy functionalized compatibilizer (Lotader™ AX8930) are added in different concentrations.

The adhesion properties are tested by injection molding

- 5 30 x 30 x 2mm plaques of the thermoplastic elastomer composition against the small side of 30 x 30 x 2mm plaques of different substrates (polycarbonate, ABS and polypropylene) at a temperature of 240°C. The final part is 60 x 60 x 2 mm. The adhesion after injection molding is evaluated by cutting test bars across the interface and measuring the mechanical strength of the 2K test bar. Besides the
- 10 adhesion strength, the type of failure is classified as either adhesive or cohesive.

The mechanical and adhesion properties are shown in table 2.

WO 02/055599

PCT/NL02/00006

- 11 -

Table 2

	2	3	4	5	6
Composition					
Amitel™ EM400	60	50	40	30	20
TPV-40	25	35	45	50	60
Lotader™AX8930	15	15	15	20	20
Mechanical properties					
Hardness [Shore A]	80	75	68	63	55
Tensile strength [Mpa]	7.9	6.7	5.0	4.7	4.0
Elongation [%]	490	375	280	200	180
C. set 72h/23°C [%]	29	30	30	31	31
C. set 22h/70°C [%]	46	48	51	48	45
Adhesion to PC [Mpa]	5.9	5.0	3.7	3.4	2.9
Type of failure	Cohesive	Cohesive	Cohesive	Cohesive	Cohesive
Adhesion to ABS [Mpa]	5.1	4.3	3.1	2.6	2.1
Type of failure	Cohesive	Cohesive	Cohesive	Cohesive	Cohesive
Adhesion to PP [Mpa]	5.6	4.9	3.8	3.7	3.1
Type of failure	Cohesive	Cohesive	Cohesive	Cohesive	Cohesive

- Table 2 shows that the use of a larger amount of Amitel™EM400 in the thermoplastic elastomer composition according to the invention results in stronger adhesion to both the polar and the apolar substrates. In all cases the type of failure is cohesive.

Examples 7 to 9

- TPV40 is produced by melt blending 45% EPDM, 10% PP, 35% paraffinic oil, 0.5% phenolic resin, 0.5% stannous chloride and 0.5% stabilizer on a 40mm co-rotating twin screw extruder at a melt temperature of 250°C. in the

WO 02/055599

PCT/NL02/00006

- 12 -

same extrusion step the epoxy functionalized compatibilizer (Lotader™ AX8930) is added.

In a second step the thermoplastic elastomer composition is produced by melt blending TPV-40 (including an epoxy functionalized compatibilizer, Lotader™ AX8840) with different copolyether esters (Amitel™ EM400, EM550, EM630) on a 30mm co-rotating twin screw extruder at a melt temperature of 230°C.

The adhesion properties are tested by injection molding 2mm plaques of the thermoplastic elastomer composition against 2mm plaques of different substrates (polycarbonate, ABS, polypropylene, Amitel™ EM 550 and polybutylene terephthalate) at a temperature of 240°C. The adhesion after injection molding is classified as no, poor or strong adhesion. In addition, the type of failure is classified as either adhesive or cohesive.

The mechanical and adhesion properties are shown in table 3.

15

WO 02/055599

PCT/NL02/00006

- 13 -

Table 3

	7	8	9
Composition			
Amitel™EM400	50		
Amitel™ EM550		50	
Amitel™ EM630			50
TPV-40	40	40	40
Lotader™AX8930	10	10	10
Mechanical properties			
Hardness [Shore A]	75	86	93
Tensile strength [Mpa]	4.9	5.8	7.0
Elongation [%]	370	300	220
Adhesion to PC	Strong	Strong	Strong
Type of failure	Cohesive	Cohesive	Cohesive
Adhesion to ABS	Strong	Strong	Strong
Type of failure	Cohesive	Cohesive	Cohesive
Adhesion to PBT	Strong	Strong	Strong
Type of failure	Cohesive	Cohesive	Cohesive
Adhesion to Amitel™EM550	Strong	Strong	Strong
Type of failure	Cohesive	Cohesive	Cohesive
Adhesion to PP	Strong	Strong	Strong
Type of failure	Cohesive	Cohesive	Cohesive

Table 3 shows that the mechanical properties are influenced by the use of different types of Amitel™. The adhesion properties, however, are strong for all the substrates. In all cases cohesive adhesion is obtained.

WO 02/055599

PCT/NL02/00006

- 14 -

CLAIMS

1. Thermoplastic elastomer composition, characterized in that the composition contains:
 - 5 a. a dynamically vulcanized thermoplastic elastomer containing a polypropylene polymer and an at least partly dynamically vulcanized rubber
 - b. a thermoplastic polyester block copolymer
 - c. a compatibilizer.
- 10 2. Thermoplastic elastomer composition according to claim 1, characterized in that the composition contains 20-80 parts (a), 80-20 parts (b) and 1-40 parts (c), the sum of the parts (a+b+c) being 100.
3. Thermoplastic elastomer composition according to either of claims 1-2, characterized in that the composition contains 30-70 parts (a), 70-30 parts (b) and 5-20 parts (c), the sum of parts (a+b+c) being 100.
- 15 4. Thermoplastic elastomer composition according to claim 1, characterized in that the polypropylene polymer is a propylene homo- or copolymer.
5. Thermoplastic elastomer composition according to claim 1, characterized in that the rubber is an EPDM or EPM copolymer.
- 20 6. Thermoplastic elastomer composition according to claim 1, characterized in that the at least partly dynamically vulcanized rubber has a gel content that is higher than 80%.
7. Thermoplastic elastomer composition according to claim 6, characterized in that the at least partly dynamically vulcanized rubber has a gel content that is higher than 95%.
- 25 8. Thermoplastic elastomer composition according to claim 1, characterized in that the thermoplastic polyester block copolymer is a polyether ester block copolymer.
9. Thermoplastic elastomer composition according to claim 1, characterized in that the compatibilizer is a functionalized polymer.
- 30 10. Thermoplastic elastomer composition according to claim 9, characterized in that the functionalized polymer is an epoxy or acid functionalized polymer.
11. Thermoplastic elastomer composition according to claim 10, characterized in that the epoxy functionalized polymer is an epoxy-
- 35

WO 02/055599

PCT/NL02/00006

- 15 -

functionalized olefin polymer.

12. Molded article that contains the thermoplastic elastomer composition according to any one of claims 1-11.
 13. Molded article comprising a substrate part and a part that comprises the thermoplastic elastomer composition according to any of claims 1-11
- 5 whereby the parts are being adhered.